




DESCRIPTION			
Total thickness	EN ISO 24346	mm	2.00
Thickness of wearlayer	EN ISO 24340	mm	0.85
Weight	EN ISO 23997	g/m ²	2460
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : Pendulum Test (dry & wet)	BS 7976-2	PTV	> 36
Surface roughness	-	µm	Rz ≥ 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10
Slip resistance wet : rampt test with water	DIN 51097	class	B
Slip resistance – ramp test	EN 13845 (annex C)	class	ESf-ESb
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	-	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (norm)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (average measured value)	-	mm	≤ 0.05
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (MRSA) (1)	ISO 22196	-	> 99% Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100 micrograms
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection